



## Product Description

<b>1. Product Name</b>	<b>Basetrac® Duo-C PET 40 B15</b>		
<b>2. Product Description</b>	Biaxial geogrid plus nonwoven geotextile for base reinforcement with protective polymer coating (grid)		
<b>3. Raw Materials used</b>			
Raw Material of the geogrid:	MD / CMD	PET	
Raw Material of the nonwoven:		150 g/m <sup>2</sup> PP	
Type of Coating:		polymer	
<b>Technical data</b>			
<b>01. Mass per unit area</b> (DIN EN ISO 9864)		g/m <sup>2</sup>	≅ 410
<b>02. Nominal Tensile Strength</b> (DIN EN ISO 10319)	MD CMD	kN/m kN/m	≥ 40 ≥ 40
<b>03. Strain at Nominal Tensile Strength</b> (DIN EN ISO 10319)	MD CMD	% %	≤ 10 ≤ 10
<b>04. Mesh Size of the Geogrid</b>		mm	25 x 25
<b>05. Opening Size of the Nonwoven</b> (DIN EN ISO 12956)		µm	≅ 100
<b>06. Water Permeability Index Normal to the Plane</b> (nonwoven) (EN ISO 11058)		m/s	≅ 90 x 10 <sup>-3</sup>
<b>07. Standard Roll Dimensions</b> (width x length)		m x m	5,00 x 100
<b>08. Durability</b> (acc. to EN 13249: 2015 ff.)	Predicted to be durable for 100 years in natural soils with 4 ≤ pH ≤ 9 and soil temperatures ≤ 25 °C.		